

**KLASSIC**  
**Exterior Emulsion Paint**

**Salient features**

- ❖ It is based on tough and flexible co-polymer emulsion.
- ❖ Its unique product design gives good protection against alkali, U.V., water, algae, fungus, etc.
- ❖ It is best suited for exterior application in dry or moderately humid climatic conditions. It can also be used for interiors.

**TECHNICAL DATA**

**Areas of Application** : Cement Plasters, Fiber boards, RCC.

**Method of Application** : Brush, Roller or Spray.

**Consistency** : Smooth and free flowing.

**Finish** : Smooth and Matt.

**Thinner recommended** : Potable water.

**Supply Viscosity on Stormer** : 90±10 krebs at 30°C

**Drying at 30°C & 60% r.h**

**Surface Dry** : Less than 30 minutes  
**Hard Dry** : Minimum 4hrs

**Recoating Period** : 4-6 hrs at 30°C and 60% R.H.

**Spreading capacity** : At thinner ratio of 4 parts of paint & 3 parts of water by volume or 1 Kg. Paint & 500 Gm. Water is 5 to 6 Sq. mtrs/ltrs/2 coats depending on shades

**Minimum dft** : 40 - 45 microns/coat

**Packs Available** : 20 Ltrs., 10 Ltrs., 4 Ltrs, 1 Ltr

## **DIRECTIONS FOR USE :**

For desired performance adequate thickness of paint deposition and surface preparation is of utmost importance.

### **Surface preparation :**

Ensure that the surface to be painted is free from any loose paint dust, grease and growth of algae, fungus or moth.

Use of wire brush and water is recommended for this purpose.

Surface imperfections such as cracks, holes etc should be repaired using white cement and fine sand in proper proportion to stop leakage or seepage.

### **Application :**

For repainting job 2 coats with recommended thinning ratio are adequate however for newly plastered surface Primer has to be used. The Primers recommended are Godavri W/T Primer, Supremcem Cement Paint or Colorsol Stabilising Solution followed by two coats of Klassic Exterior Emulsion Paint. Minimum 4 hrs. gap is required between two subsequent coats.

Dilution ratio of paint with portable water can be altered taking in to consideration the nature of surface, climate & dft required, maximum dilution permitted for top coats of paint is 1 part of water to 1 part of paint by volume.

Horizontal surface should be given one extra coat for better protection.

Do not over thin or overextend the brush.

## **TECHNICAL AID SERVICE PROVIDED ON REQUEST**

Mfd. by : **GODAVRI PAINTS PVT. LTD.**

Tulsiram Gupta Mills Estate, Darukhana, Reay Road, Mumbai 400 010.

Tel.: 2372 3227 / 1249 . 2379 0135 Fax: 2377 5814

E-mail : admin@godavaripaints.com Website : www.godavaripaints.com

**DEPOTS : AHMEDABAD, BHIWANDI, PUNE, VADODARA, BANGLORE**

**C & F / AGENTS : KANPUR, KOLHAPUR**

### **DISCLAIMER FOR PRODUCTS :**

The information presented in this publication, including technical data, details, pictures, illustrations, suggested procedures and suggested specifications, presented in this publication are for general information and representational purpose only. The information contained herein is subject to change without notice while every effort has been made to insure its accuracy, this information should not be used or relied upon for any specific application without independent professional examination and verification of its accuracy, suitability and applicability. The user shall be solely responsible for the selection, use, efficiency and suitability of the information, and anyone making use of the information does so at his own risk and assumes any and all liability resulting from such use. The information is provided on an "as is" basis and Godavri Paints Pvt. Ltd. disclaims any and all express or implied warranties of merchantability, fitness for any general or particular purpose or freedom from infringement of any patent, trademark, copyright, or proprietary right in regard to information or products contained or referred to herein. Nothing herein contained shall be construed as granting a license, express or implied under any patent, trademark, or copyright. In no event shall Godavri Paints Pvt. Ltd. be liable to user for any indirect, special, consequential or incidental damages arising out of the use, the results of use or inability to use the information.

The names of the products and trademarks are copyrights of Godavri Paints Pvt. Ltd. and its business partners who own the products developed by them that are marketed by Godavri Paints Pvt. Ltd.