

PEARL
Acrylic Exterior Paint

Salient features :

- ❖ Based on Pure acrylic emulsion.
- ❖ Designed meticulously to resist, U.V degradation, cracking, flaking, etc.
- ❖ It has excellent breathability which protects underlying surface.
- ❖ Reinforced with fungicide biocide and bactericide it curbs the growth of fungus and algae on application and bacteria's during storage.

TECHNICAL DATA

Areas of Application	:	Masonry, Fiber boards, RCC.
Methods of Application	:	Brush, Roller or Spray.
Consistency	:	Smooth.
Finish	:	Smooth with slight sheen
Thinner recommended	:	Potable water.
Supply of Viscosity on Stormer at 30°C	:	100±10krebs
Drying at 30°C & 60%		
	Surface Dry :	less than 30 minutes
	Hard Dry :	Minimum 4 hrs
Recoating Period	:	Minimum 4hrs at 30°C and 60% R.H.
Spreading capacity	:	At thinner ratio of 100:40 by volume of Paint ; water is 5 to 6 ^{sq} .mtrs/ltrs/2 coats depending on shade and surface.
Minimum dft	:	(at above spreading rate) 40 to 45 microns/coat
Packs Available	:	1 Ltrs., 4 Ltrs., 20 Ltrs.

DIRECTIONS FOR USE :

For desired performance adequate thickness of paint deposition and surface preparation is of utmost importance.

Surface preparation :

Ensure that the surface to be painted is free from any loose paint dust, grease and growth of algae, fungus or moth.

Use of wire brush and water is recommended for this purpose.

Surface imperfections such as cracks, holes etc should be repaired using white cement and fine sand in proper proportion to stop leakage or seepage.

Application :

For repainting job 2 coats with recommended thinning ratio are adequate however for newly plastered surface priming coat with 100% dilution by volume (with water) or 1 coat of Supremcem Cement Paint or 1 coat of Colorsol followed by 2 coats as above is necessary. Minimum 4 hrs gap is required between two subsequent coats.

Dilution ratio of paint with potable water can be altered taking in to consideration the nature of surface, climate & dft required, maximum dilution permitted for top coats of paint 100 : 40 by volume of paint to water.

Horizontal surface should be given one extra coat for better protection.

Do not over thin or overextend the brush.

You can also use our colorsol Stabilising Solution in place of surface priming coat.

TECHNICAL AID SERVICE PROVIDED ON REQUEST

Mfd. by : **GODAVRI PAINTS PVT. LTD.**

Tulsiram Gupta Mills Estate, Darukhana, Reay Road, Mumbai 400 010.

Tel.: 2372 3227 / 1249 . 2379 0135 Fax: 2377 5814

E-mail : admin@godavaripaints.com Website : www.godavaripaints.com

DEPOTS : AHMEDABAD, BHIWANDI, PUNE, VADODARA, BANGLORE

C & F / AGENTS : KANPUR, KOLHAPUR

DISCLAIMER FOR PRODUCTS :

The information presented in this publication, including technical data, details, pictures, illustrations, suggested procedures and suggested specifications, presented in this publication are for general information and representational purpose only. The information contained herein is subject to change without notice while every effort has been made to insure its accuracy, this information should not be used or relied upon for any specific application without independent professional examination and verification of its accuracy, suitability and applicability. The user shall be solely responsible for the selection, use, efficiency and suitability of the information, and anyone making use of the information does so at his own risk and assumes any and all liability resulting from such use. The information is provided on an "as is" basis and Godavri Paints Pvt. Ltd. disclaims any and all express or implied warranties of merchantability, fitness for any general or particular purpose or freedom from infringement of any patent, trademark, copyright, or proprietary right in regard to information or products contained or referred to herein. Nothing herein contained shall be construed as granting a license, express or implied under any patent, trademark, or copyright. In no event shall Godavri Paints Pvt. Ltd. be liable to user for any indirect, special, consequential or incidental damages arising out of the use, the results of use or inability to use the information.

The names of the products and trademarks are copyrights of Godavri Paints Pvt. Ltd. and its business partners who own the products developed by them that are marketed by Godavri Paints Pvt. Ltd.